



Twin Ports Testing Inc.

1301 N. 3rd Street • Superior, WI 54880 • 715-392-7114 • Fax 715-392-7163
218-722-1911 • 800-373-2562 • www.twinportstesting.com

Corinth Wood Pellet
Po Box 407
Corinth, Maine 04427

Date Received: 7/22/2009

Date Tested: 7/23/2009

Purchase Order #:

Attn: Samantha Eldredge

Sample Log Number: 09C2068

Sample Designation: Pellet Bag

	MOISTURE & ASH FREE	MOISTURE FREE	AS RECEIVED	UNITS	METHOD
Moisture Total			6.55	% wt.	ASTM E871
Ash		0.50	0.47	% wt.	ASTM D1102
Sulfur		0.010	0.009	% wt.	ASTM D4239
Heating Value	8182	8141	7608	Btu/lb	ASTM E711

	MDL	MOISTURE FREE	AS RECEIVED	UNITS	METHOD
Chlorine	10	10	9	mg/kg	ASTM D6721

	AS RECEIVED	UNITS		AS RECEIVED	UNITS
Bulk Density	43.20	lbs/cu.ft.	Fines	0.17	% wt.
Sample Above 1.50 In	0.0	%	Durability Index	98.7	
Maximum Length	2.288	inch	Stated Bag Wt.	40.0	lbs
Diameter, Range	0.253 to 0.265	inch	Actual Bag Wt.	40.4	lbs
Diameter, Average	0.259	inch			

Prepared By: *Heaven Archer*

Date: 7/24/09